



www.multicretesystems.com

MULTIGROUT CB TECHNICAL DATA SHEET

Resistant to Water Washout

DESCRIPTION

MULTIGROUT CB is an un-sanded, cement-based expanding grout containing silica fume (microsilica) and other carefully selected additives. MultiGrout CB gains strength quickly and resists water washout, making it ideal for anchoring tendons, cables and bolts into soil or rock media.

USES

- MULTIGROUT CB can be used for most grouted anchor requirements, including:
 - Earth tiebacks for excavation and slope stabilization.
 - Rock bolts or soil anchors in tunnel support systems.
 - Cable bolting.
 - Soil or rock tendons used for anchoring piles or foundation structures. Infill of pipe piles.

ADVANTAGES

- **High early strength:** MULTIGROUT CB has superior early strength gain compared to Type 30 grouts, allowing early tensioning of anchors. It has comparable strength gain to high alumina grouts, but does not experience strength regression.
- **Resistance to water washout:** MULTIGROUT CB has excellent cohesive properties. It resists washout or dilution by water and thus can be used in wet ground conditions and still retain its excellent physical properties.
- **Reduced Grout Times:** MULTIGROUT CB has thixotropic properties. It tends to gel after placement or pumping. This gelling action prevents the loss of grout in porous or fractured geology.

Consistency Recommended Water Qty/20 kg bag

Pumpable: 0.33 wcm 6.6 litres (1.7 US gal)
Flowable: 0.4 wcm 8.0 litres (2.1 US gal)

Over watering will result in compressive strengths and inferior physical properties.

APPLICATION

Step 1: Mix MULTIGROUT CB to the consistency required for placement. MULTIGROUT CB's thixotropic properties make the grout appear thick and cohesive when in fact it is quite pumpable.

Step 2: Introduce potable water into a high shear mixer and then add MULTIGROUT CB while operating at medium speed.

Step 3: Mix at high speed for a minimum of five minutes. Ten minutes in mortar style mixers

PACKAGING

MULTIGROUT CB is packaged in 20 kg bags. All MULTIGROUT CB packaged materials can be custom packaged to meet specific project requirements.

SAFETY PRECAUTIONS

MULTIGROUT CB contains Portland cement and carefully selected additives. Normal safety wear such as dust mask and rubber gloves used to handle conventional cement based products should be worn. Safety Data Sheets (SDS) are available.

LIMITATIONS

Adhering to recommended water additions is very important. Exceeding the maximum recommended water content per sack will result in inferior physical properties.

TECHNICAL DATA

The data outlined below is representative of typical values achievable under controlled laboratory conditions. Results obtained in the field may vary from those stated.

Typical Properties at Flowable Consistency
(Corps of Engineers CRD-C821 and ASTM C1107)

Flow:	22 seconds	
Expansion, % volume:	At 3 & 14 days At 28 days	
	Not greater than at 28 days 0.4 maximum (0.24 Typical)	
Setting Time:	15 hours at 20°C	
Compressive Strength:	MPa (psi)	
	Pumpable	Flowable
At 24 hours:	49.7 (7208)	40.6 (5888)
At 48 hours:	59.0 (8557)	48.2 (6990)
At 7 days:	67.1 (9732)	54.8 (7948)
At 28 days:	83.1 (12053)	67.9 (9848)